

## Reflective Films

Type of Films	Ply	MT	SET	SEA	SER	VLT	VLA	VLRI	VLRE	UVR	SC	SHR	TSER	GR	E	UV
Bronze Reflective 30	2	2 Mil	32%	51%	17%	30%	57%	24%	13%	99%	0.53	47%	53%	67%	0.73	1.08
Bronze Reflective 40	2	2 Mil	44%	47%	9%	42%	48%	9%	10%	99%	0.66	34%	43%	53%	0.82	1.06

- **MT** : Mil Thickness ● **SET** : Solar Energy Transmittance ● **SEA** : Solar Energy Absorbance ● **SER** : Solar Energy Reflectance
- **VLT** : Visible Light Transmittance ● **VLA** : Visible Light Absorbance ● **VLRI** : Visible Light Reflected Interior
- **VLRE** : Visible Light Reflected Exterior ● **UVR** : Ultra Violet Rejected ● **SC** : Shading Coefficient ● **SHR** : Solar Heat Reduction
- **TSER** : Total Solar Energy Rejection ● **GR** : Glare Reduction ● **E** : Emissivity ● **UV** : U-Value ● **T** : Thickness ● **VLR** : Visible Light Reflectance
- **UVT** : Ultra Violet Transmittance ● **UF** : U Factor (BTU /HR./SQ.FT.)