

Reflective Films

Type of Films	Ply	MT	SET	SEA	SER	VLT	VLA	VLRI	VLRE	UVR	SC	SHR	TSER	GR	E	UV
Silver Reflective 20	2	2 Mil	13%	34%	53%	18%	24%	59%	58%	99%	0.25	75%	78%	80%	0.64	1.01
Silver Reflective 35	2	2 Mil	28%	35%	37%	36%	26%	38%	38%	99%	0.43	57%	63%	60%	0.72	1.05
Silver Reflective 50	2	2 Mil	38%	36%	26%	49%	25%	27%	26%	99%	0.56	44%	52%	46%	0.78	1.07

- **MT** : Mil Thickness ● **SET** : Solar Energy Transmittance ● **SEA** : Solar Energy Absorbance ● **SER** : Solar Energy Reflectance
- **VLT** : Visible Light Transmittance ● **VLA** : Visible Light Absorbance ● **VLRI** : Visible Light Reflected Interior
- **VLRE** : Visible Light Reflected Exterior ● **UVR** : Ultra Violet Rejected ● **SC** : Shading Coefficient ● **SHR** : Solar Heat Reduction
- **TSER** : Total Solar Energy Rejection ● **GR** : Glare Reduction ● **E** : Emissivity ● **UV** : U-Value ● **T** : Thickness ● **VLR** : Visible Light Reflectance
- **UVT** : Ultra Violet Transmittance ● **UF** : U Factor (BTU /HR./SQ.FT.)